

420 South 38<sup>th</sup> Avenue St. Charles, IL 60174 Tel: (630) 762-0100 Fax: (630) 762-0111

## **American Powder Coatings, Inc.**

## PRODUCT DATA SHEET

PRODUCT DESCRIPTION: POLYESTER/TGIC PRODUCT NUMBER: T1-BK15-T COLOR: BLACK TEXTURE

## PHYSICAL PROPERTIES

| SPECIFIC GRAVITY:                                    | 1.50 <u>+</u> .05     |  |
|--|-----------------------|--|
| GEL TIME @ 400 °F:                                   | 120-130 sec           |  |
| FLEXIBILITY:   |                       |  |
| IMPACT DIRECT:                                       | 160 inch/pounds- Pass |  |
| IMPACT REVERSE: 160 inch/pounds- Pass                |                       |  |
| GLOSS $(60^{\circ})$ :                               | < 10                  |  |
| THICKNESS:   | 2.0 - 3.0 mils        |  |
| PENCIL HARDNESS:                                     | H - 2H                |  |
| MEK RESISTANCE (Double-Rubs): 20- Softens & Recovers |                       |  |
| VOLATILE ORGANICS (VOCs): $< 5\%$                    |                       |  |
| CONICAL MANDREL:                                     | 100% Pass             |  |
| ADHESION TEST:                                       |                       |  |
| CROSS HATCH:   | 100% Pass             |  |
| SALT SPRAY:  | 1,000 Hrs.*           |  |
| HUMIDITY:  | 1,000 Hrs.*           |  |
| QUV:   | 1,000 Hrs.*           |  |
| *** with proper pretreatment and application ***     |                       |  |

## APPLICATION

| METHOD:                            | Electrostatic Spray            |
|------------------------------------|--------------------------------|
| VOLTAGE:                           | 70 KVA                         |
| CURE CYCLE:                        | 10 min @ 400 °F:               |
| <b>RECOMMENDED FILM THICKNESS:</b> | 2.0 - 3.0 mils                 |
| SUBSTRATE:                         | CRS/Bonderite 1000             |
| CALCULATED COVERAGE (@ 1 mil):     | 128 sqft                       |
| USAGE:                             | Functional/Decorative Coatings |

STORAGE CONDITIONS: Store in cool, dry area (max. 80 °F)

The above information is considered to be accurate based on data received from our raw material suppliers. While this information is believed to be reliable, no warranty is issued for the accuracy of this data or for which American Powder Coatings, Inc. assumes legal liability for results to be obtained from the use thereof.